

ULTRAGuard™

WerkMaster Chemicals Inc.

1448 Charlotte Road, North Vancouver, BC, Canada V7J 1H2

tel: 604.629.8700 | fax: 604.990.9538 | www.werkmaster.com

DESCRIPTION

UltraGuard is a stone sealer and surface wear protector for all stone surfaces

INTENDED USE

- Penetrating Sealer
- Polish Protectant

PRODUCT FEATURES

- Stone sealer providing stain protection against water, oil and acid based staining agents.
- Slip Resistance.

PHYSICAL PROPERTIES

- Flash Point 248°F
- Viscosity Milky
- Colour White
- Type of Solids Modified Acrylic
- Boiling Range
High N/A
Low 212°F
- Odour Moderate

LIMITATIONS OF USE

For industrial/professional use only.

ORDERING INFORMATION

Call WerkMaster toll free:
1.866.373.WERK

SURFACE PREPARATION

Floor must be clean and dry and free from all other sealers other than UltraHard.

MIXING INSTRUCTIONS

No mixing required.

APPLICATION INSTRUCTIONS

UltraGuard may be applied from 200 – 3000 grit and after UltraHard densifier has dried.

- 1 Clean floor thoroughly by dust mopping, sweeping and or vacuuming and then damp mopping or autoscrubbing using UltraClean Hi-Lite neutral cleaner.
- 2 Rinse floor and allow to dry.
- 3 Apply 1 thin even coat of UltraGuard using a microfibre applicator and allow 45 minutes to dry.
- 4 If buffing is desired, the floor may be buffed using the WerkMaster machine with Random Orbital Heads and Hogs Hair or Pink Polishing pads.

STORAGE

DO NOT allow to freeze. DO NOT store above 100°F

COMPLIANCES

VOC 93gm/L Calif. Compliant.

CHEMICAL RESISTANCE

A stone panel was cleaned, etched with HCl solution, and then dried for 24 hours. Three coats of UltraGuard were brush applied on the stone panel at an application rate of approximately 800–1000 ft/Gal. The film was allowed to dry 4 days prior to chemical testing. The spots were applied, covered with a watch glass, and allowed to stand for 24 hours. Results were evaluated upon removal of the watch glass.

Chemical	24 Hr. Spot Test Result	Chemical	24 Hr. Spot Test Result
Antifreeze	10	Moneethanolamine.....	10
Gasoline	5D*	50% Sodium Hydroxide	10
Bearing Grease	10	Isopropyl Alcohol	8
Brake Fluid.....	3D*	Methanol.....	10
Transmission Fl.....	10	d-Limonene	1
Motor Oil.....	10	Mineral Spirits.....	10
Bleach.....	10	Butyl Cellosolve.....	1
37% Hydrochloric Acid	9	MEK	1
37% Sulfuric Acid.....	10	1% Tide Laundry Soap.....	10
10% Ammonium Hydroxide	10	10% Trisodium Phosphate	10

*D = Dense blisters. Scale Rating = 1–10 (1 = Worst, 10 = Best).

PRECAUTIONS

Please refer to the appropriate material safety data sheet (MSDS) prior to using this product.

For technical assistance, please call 1-866-373-WERK
FOR INDUSTRIAL/PROFESSIONAL USE ONLY

Keep containers closed when not in use and upright to prevent leakage. DO NOT take internally. Wash hands after using and before eating. Keep out of reach of children. Dispose of according to law and local regulations.

WARRANTY

WerkMaster Chemicals Inc. will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

DISCLAIMER

All information on this data sheet is based on laboratory testing and is not intended for design purposes. WerkMaster Chemicals Inc. makes no representations or warranties of any kind concerning this data.

Taking it to the Wall!